



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

TECHNICAL DATA SHEET

CHAMÄLEON PLASTIC PRIMER

Article number:	26014
Intended use:	Car refinishing Product/ Preparation
General characteristics:	High quality, fast drying plastic primer to treat surfaces, treated and untreated, of several types of plastic.
Product characteristics:	<ul style="list-style-type: none">• Fast drying• Excellent adhesion• Re-sprayable with all lacquer systems
Physical and Chemical	Characteristics
Contents	400 ml
Base	Polyolefine resin
Colour	Transparent
VOC-content	Approximately 99 % w/w
Solid content	Approximately 1 % w/w
Coverage	2 to 3 m ²
Re-sprayable	After 10 to 15 minutes
Usage:	Before use, carefully read the directions on the packaging and act accordingly.
Pre Treatment:	The surface should be clean, dry and free of grease. When desired, slightly sand the surface, grain 600.
Treatment:	The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

treated approximately 25 to 30 centimeter.

Apply the plastic primer in maximum two (2) thin layers.

After use:

After drying, without sanding, re-sprayable with all lacquer systems.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:
e-mail: info@chamaeleon-produktion.de
See information on safety in Safety Data Sheet.*